

# EXHIBIT 3

Compounds with negligible Reactivity with OH Radicals

6

Non-photochemically reactive compounds # 1

Zero-volatile organic compounds - Hydrocarbon based

C-12-C18 mixture  
(approx 12% alkyl content) Solvent Solubility Resins (10 Gms)

100 Gms Solvent	PS		
1	I	Styrene-Butadiene	Elastomeric
2	S	Styrene	"
3	I	Styrene-Isoprene-Styrene	"
4	I	Nitrocellulose	Coatings
5	I	Alkyd	"
6	I	Silicone	"
7	I	Cellulose Acetate Butyrate	"
8	S	Acrylic	"
9	I	Terpene	Tactifiber
10	S	Polychloroprene	Elastomeric
11	S	Alkyl Ester	Tactifiber
12	I	Carboxylic Terpene	"
13	PS	PVC	Elastomer
14	I	Epoxy	Resin
15	I	Chlorinated Rubber	"
16	I	Phenolic	"
17	S	Alkyd	"
18	I	Urethane	"

S = Soluble  
I = Insoluble

PS = Partially Soluble

Not as strong as others  
But still useful for Adhesives,  
Inks and some coatings.